TECHNICAL DATA SHEET



Hyperform[®]-RS

TYPICAL PERFORMANCE CHARACTERISTICS*

- Compressive Strength (ASTM C39) 30 minutes >1.200 psi | 8.27 MPa 1 hour >2.500 psi | 17.24 MPa 1 day >4.000 psi | 27.58 MPa 28 days >7.000 psi | 48.26 MPa
- Bond Strength (ASTM C882) 28 day >3,000 psi | 20.68 MPa
- Shrinkage (ASTM C596) $28 \text{ Days} \le 0.02\%$
- * The values stated in inch-pound units are to be regarded as the standard. The values given in International System are for information

FEATURES AND BENEFITS

- Rapid-setting, 3 to 5 minutes
- · High early and ultimate strengths
- Non-Shrinking
- No Calcium Chloride
- · Ready to use, just add water
- · Excellent resistance to freeze thaw

WARRANTY

Quadex, LLC warrants its products to be free of defects in material and workmanship. Unless superseded by project specifications and terms agreed upon in writing between installer and Quadex prior to bid, if within one year from purchase, any Quadex, LLC product is proven defective, the company will replace said product or refund its purchase price at its sole discretion. The company's obligation shall be limited solely to such replacement or refund. There are no other warranties by Quadex, LLC, expressed or implied. There is no warranty if Quadex products are used contrary to Quadex, LLC's written directions.



Rapid Set High Early Strength Patching Material

DESCRIPTION

Hyperform[®]-RS is a one component, rapid setting, high early strength patching material designed for repairing vertical and horizontal concrete and masonry structures.

RECOMMENDED FOR

- · Filling large voids in manhole walls
- · Reconstructing inverts
- · Concrete repair and patching
- Pipe repair

PACKAGING

Hyperform is supplied in 50 lb. | 22.7 kg. plastic pails.

One 50 lb. bucket of Hyperform-RS will yield approximately .40 cu. ft. and will cover 9.6 sq. ft. at a $\frac{1}{2}$ in. thickness.

APPLICATION INFORMATION

Prepare surface to be patched by removing all loose concrete by using an air or electric hammer. Next, sandblast or water blast surface to clean away all contaminants, such as oil, chemicals, or dust. Then rinse with potable water to remove all remaining dirt, sand and loose debris.

Mix Hyperform with clean potable water at a rate of 0.8 gallon per 50 lb. bucket. If needed, Hyperform can be extended with 3/4" aggregate at a rate of 20 lbs. per bucket.

PRECAUTIONS

Avoid eye contact or prolonged contact with skin. Wash thoroughly after use. Persons using Hyperform should wear necessary eye protection, dust mask and rubber gloves. Read all product labels and technical literature.